

POOLTEK PRIMER

One-component bonding primer specifically for nonporous surfaces



DESCRIPTION

Alcoholic solution of organo-silanes/siloxanes, suitable for the preventive treatment of non-porous surfaces such as glass, ceramics, stoneware, porcelain, iron, aluminum, etc. suitable for promoting the adhesion of silicone and polyurethane rubbers, as well as epoxy, polyurethane, polyurea, acrylic formulations, on the same substrates.

MEDIA PREPARATION

Remove any residue of dirt, dust, oils, greases, waxes, previous coatings, crumbly and dilapidated parts.

In the case of joints, cracks, etc.

APPLICATION

Apply the product with a brush or roller or spray perfectly clean and until saturated the entire surface to be treated. After applying pooltek primer wait 24 hours (at 20°C) before applying POOLTEK TOP.

TECHNICAL FEATURES

(at +25°C and 60% U.R.)

Appearance	colored liquid
Odor	alcoholic
Viscosity	10 - 20 cps
Specific weight	0,90 ± 0,02 g/cm ³
Application	brush / spray / roller
Drying	> 2 hours
Yield	about 100 g/m ² depending on the support

CLEANING AND MAINTENANCE

Clean tools first with rags or paper sheets, then with alcohol.

PACKAGING AND STORAGE

5-10-20 kg tanks

Three months in the original sealed packages, in a dry place, at temperatures between 5°C and 35°C.

LEGAL NOTICES

The information contained in this technical data sheet, while representing the most advanced stage of knowledge, does not exempt the user from carrying out accurate preliminary tests under the usual conditions of use and exercise. We therefore decline all responsibility for improper use of the product.



TEKNA CHEM S.p.A.

Headquarters: Renate (MB) - Via Sirtori, z.i. 20838 - Tel. +39 0362.91.83.11

Web: www.teknachemgroup.com - E-mail: info@teknachemgroup.com - Fax: +39 0362.91.93.96

